



1071

Protan as, Postboks 420, N-3002 Drammen

06

1071-CPD-1142

DoP1010

EN 13956Product name: Protan EX-A

PVC membrane with internal synthetic fabric as reinforcing material and a polyester fleece backing.

Thickness 1,5 mm

Exposed fully adhered applications

External fire performance in accordance with EN 13501-5:2007+A1:2009: B_{ROOF} (t*)

Reaction to fire: Class E

Watertightness (10kPa): Pass

Tensile strength: 1100 N/50mm

Elongation: 15%

Tear resistance: 300N

Dimensional stability: +/-0,5%

Resistance by static loading: 20kg

Resistance by impact 23°C: 700 mm

Resistance by impact -10°C: 8mm

Peel resistance of joints: 150N/50mm

Shear resistance of joints: 1000N/50mm

Foldability at low temperature: -25°C

Information about chemical resistance: see Annex C

*separate documentation for fire classification is available on request

CE-marking on labels:



1071-CPD-1142

EN 13956**DoP1010**www.protan.com